



SCREEN PRINTING

SOLVENT INK

POLYCOLOR EXTRA-OPAQUE

Matt air drying ink intended for printing on polycarbonate and on polyester. This ink does not adhere to PVC and is not thermoformable.

CAUTION: POLYCOLOR EXTRA OPAQUE ink cannot be mixed with the POLYCOLOR standard serie.

Use

The **EXTRA-OPAQUE** inks are reserved as the last opacifying layer for the front sides of treated polycarbonate and polyester.

Specifications

- | | | | |
|------------------------------|--|--|--|
| ➤ Appearance: | matt | | |
| ➤ Average density: | 1.35 | | |
| ➤ Viscosity: | 10 ± 2 Pa.s | | |
| ➤ Drying: | <ul style="list-style-type: none"> • air 15 min. at 20°C | | |
| ➤ Covering power by opacity: | excellent | | |
| ➤ Coverage rate: | 20 to 25 m ² /kg with a 61 -64 mesh | | |
| ➤ Solvents: | <ul style="list-style-type: none"> • thinner 4920 • retarder 4960 | | |
| ➤ Cleaning solvents: | <ul style="list-style-type: none"> • manual 2881, 2891, NS-81 and NS-91 • washer 2881, 2899, NS-81 and NS-91 | | |
| ➤ Expiry: | refer to the label | | |

Storage and toxicology

The **EXTRA-OPAQUE** inks comply with EN 71-3 standard.

EXTRA OPAQUES		Ref. 1 kg	Ref. 5 kg
	Extra opaque white	3992040	3994040
	Extra opaque black	3992065	3994065

Attention : the «extra opaque white» and «extra opaque black» are mat

Non contractual colours and pictures
On simple request, we can propose you a color panel card displaying accurate shades.



IMP. TIFLEX 01.01.2018 - Non contractual colours and pictures - Only our Web-site is authorised to give real-time information about our inks. Paper notices are considered unwritten and no longer engage our company's responsibility once they are updated on our Web-site. Our responsibility can be engaged only if the customer has based his position on the information published on our Web-site. In all cases, the user should carry out validation tests under his own conditions before using our inks for his production. The safety data sheets are available free at: www.tiflex.com/fds



CS 30200 - 01450 PONCIN - Tél. +33 (0) 4 74 37 33 80/97
international@tiflex.fr - www.tiflex.com